

Technical data

STEULERBUTYL V10/S

Property [Unit]	Value	Testing Standard
Polymer	BIIR/CR	DIN ISO 1629
Density [g/cm ³]	1,31 ± 0,02	DIN 53479
Shore hardness A	62 ± 5	DIN 53505, ASTM D 2240
Tear resistance [MPa]	≥ 4,0	DIN 53504
Elongation at break [%]	≥ 350	DIN 53504
Temperature stability [°C]	-25 to +80	
Temperature application limit [°C]	-35 and +80	
Test voltage for leak testing [kV]	5	DIN EN 14879